



**(TAIWAN) CO., LTD.**

D/S: 2F, NO.453, CHILIN ROAD, TAIPEI TAIWAN R.O.C.  
TEL: 886-2-2593-2453/2595-2606 FAX: 886-2-2593-1655  
O.BOX: 55-1524 TAIPEI TAIWAN R.O.C.  
Mail: [bspsteve@ms3.hinet.net](mailto:bspsteve@ms3.hinet.net)

FABRIC WEIGHT: ABT. 360 G  
WIDTH: ABT. 58"

2FLOOR, No., 453 Chilim Road, Taipei, 10471, Taiwan R.O.C.

Attn: Doris Lee  
Tel: 886-2-25932453  
E-mail: [bspsteve@ms3.hinet.net](mailto:bspsteve@ms3.hinet.net)  
[bspdorist@xuite.net](mailto:bspdorist@xuite.net)

**SAMPLE DESCRIPTION** : Three (3) pieces of submitted cutting said to be:

65% Polyester 35% Cotton Twill Fabric.  
Width: ABT.58"CM  
Weight: ABT.360G/M or 242G/SQ.M.

Color : A- Jet Black  
B- DK. Brown  
C- DK. Navy

O/N. : 2135

Item No. : BSP-66TC12060

Labeled Fiber Content : 65% Polyester 35% Cotton

**SAMPLE RECEIVED** : 19<sup>th</sup> January, 2010

**TEST COMPLETION** : 20<sup>th</sup> January, 2010

**DATES**

**TEST PERFORMED AND RESULTS** : Please refer to the following pages for the tests performed in accordance with the applicant's request and their results

Conclusion: A-C

Color Fastness To Laundering: M

Key For Conclusion: M = Commercially Acceptable

**TEST SUMMARY:**

**COLORFASTNESS**

**Color Fastness to Laundering (AATCC 61-2007)**  
(Test No. 1A Method, 45 minutes at 40°C in AATCC WOB Detergent with 10 stainless steel balls, AATCC Gray Scale, multi-fiber type No. 10)

Tested Samples	Color Change	A	4.5	4.5	4.5	4.5	4.5	4.5	4.5	
		B	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5
		C	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5
		General Requirement :	Min.4	Min.3	Min.3	Min.3	Min.3	Min.3	Min.3	Min.3

Color Staining on

Modern Testing Services (HK) Ltd., Taiwan Branch  
IF. No. 649-8, Zhong Zheng Road, Hsin Zhuang City, Taipei County, Taiwan  
Tel: (02)2903-9977 Fax: (02)2903-8181 Email: [info@mts-tw.com.tw](mailto:info@mts-tw.com.tw) Website: [www.mts-global.com](http://www.mts-global.com)

USA · Italy · Germany · UK · China · Hong Kong · Taiwan · Singapore · India · Thailand · Korea · Indonesia · Australia · Turkey · Cambodia