

**Changzhou Anna Rubber & Plastic Product Co., Ltd.**

Address: No.8, Xinhua road, Qingtan area, Changjiang Middle road,  
Changzhou, Jiangsu, China  
Tel./Fax.: 86-519-86970023  
E-mail: yang@annafoam.com

<b>Name</b>	<b>Properties</b>	<b>Test result</b>
CR FOAM Closed cell	Density	170±25kg/m <sup>3</sup>
	Thermal conductivity	≤0.05W/m·K
	Shore scleroscope hardness	25±5
	Elongation	≥150%
	Compression set	≤25%
	Water absorption	<0.005%
	Compression strength	≥320kPa(25%)
	Compressibility	18%
	Rebound	60%
	Flame retardation	B1