

Stick worldwide

[HTTP://www.globalsources.com/stickworldwide.co](http://www.globalsources.com/stickworldwide.co)

FAX:+86 0752 5898221

TEL:+86 13927312771

Email:asttape@aliyun.com

Test report for AFT-9100C

Adhesive	acrylic	
Carrier	pure acrylic	
Color	transparent	
Thickness	1.0±50 μ m	
Standard roll length	33	m
Standard roll width	840	mm
Release liner	red PE	
Density	706	kg/m ³
Tensile strength to aluminum room temperature	≧ 6000	gf/cm ²
Peel adhesion to stainless steel room temperature	≧ 3900	gf/25mm
Holding power to stainless steel 80°C temperature 1000g static load	> 24	hr
Dynamic shear strength to stainless steel room temperature after 20mins	≧ 3500	gf/cm ²
to stainless steel room temperature after 24 hours	≧ 6000	gf/cm ²
temperature tolerance short term 4 hours conditioning at indicated Temperature with 100g static load	140	°C
Long term Maximum temperature where tape Supports 250g in static shear for 10000 mins	100	°C