

Changzhou Anna Rubber & Plastic Product Co., Ltd.

Address: No.8, Xinhua road, Qingtan area, Changjiang Middle road,
Changzhou, Jiangsu, China
Tel./Fax. : 86-519-86970023
E-mail: yang@annafoam.com

Name	Properties	Unit	Test result		
			ANU-20	ANU-25	ANU-30
PU FOAM Open cell	Density \geq	kg/m ³	20	25	30
	Tensile Strength \geq	kPa	100	100	100
	Elongation \geq	%	200	180	180
	75% Compression set \leq	%	5	4.5	4
	Rebound \geq	%	45	45	45
	Tearing strength \geq	N/cm	3.5	2.5	2.5