

## Physical parameters

Color: Grey

Luster: Matt

Solid content:  $\geq 60\%$

Flash point: Part A (Primer) 24 °C

Part B (Curing Agent) 27°C

Amount: 6-8 m<sup>2</sup>/ kg/paint (Thickness after drying is about 35 μ m)

Dry time: surface drying time  $\leq 2$  hours, Actual drying time  $\leq 24$ hours

Fully cured: 7 days (25°C)