



Data Sheet (MSDS)

Vulcanized Foam Rubber

Material: natural rubber (SVR3L)

Colour: Black / Beige

Process: continuous Vulcanized process

Vulcanized temperature: 160°C-170°C

Vulcanized time: 15-20 minutes

Working temperature: -40°C-160°C

Density: 550-570 g/Square meter.mm

White polyester fabric: 180-185 gsm

Sublimation temperature: 223 °C-227°C

Sublimation time: 8-15 seconds (depended on the size)

Remarks: all material shall be complied with SGS-ROHS

Derecive.