



TEXTILNÍ ZKUŠEBNÍ ÚSTAV, s.p.
(Textile Testing Institute)

Notified Body No. 1021

Cejl 480/12, Zábrdovice, 602 00 Brno, Czech Republic
issues

REPORT ON THE ASSESSMENT OF PERFORMANCE

In compliance with the Regulation (EU) No. 305/2011 of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of construction products, in the valid wording (Construction Products Regulation – CPR) – Annex V, art. 1.4 (system 3 of AVCP)

No.:

(1021/24/306)

Product:

Vinyl Flooring Tiles

Type:

Dongguan

Composition: Urethane Acrylate, Polyvinylchloride resin (19 %), Titanium Oxide, Caco 3 (75 %), Carbon Black, Stabilizer, Dot (6 %), Fiber Glass Paper, Modified Epoxy Acrylate, Acrylic Monomers, Fumed silica, Photoinitiators

Thickness: 1.5 - 3.0 mm; mass per unit area: 1060 - 2100 g/m²

Manufacturer:

Dongguan City Xinlijie New Material Co. Ltd

Building 3rd and 4th, No.6 Yinghe Road Guyong, Wanjiang, District
Dongguan City, China

Technical specification:

EN 14041:2004/ AC:2006 Resilient, textile and laminate floor coverings – Essential characteristics (art. 4.1 Reaction to fire)

Test method:

- EN 13501-1:2018 Fire classification of construction products and building elements – Part 1: Classification using test data from reaction to fire tests (EN ISO 11925-2, EN ISO 9239-1)
- EN 717-1:2004 Wood-based panels – Determination of formaldehyde release – Part 1: Formaldehyde release by the chamber method
- EN 13893:2002 Resilient, laminate and textile floor coverings – Measurement of dynamic coefficient of friction on dry floor surfaces

Classification:

Reaction to fire

class B_{fl} – s1

Formaldehyde emission

class E1

Slip resistance

class DS

Terms of report application:

This report applies to the product mentioned above and can be used only for this product. The report must only be published in unshortened form. The Manufacturer can publish a part of the report only if approved by the Notified Body 1021. The report remains in force as long as the conditions remain the same. This document does not replace type approval or certificate.

Contract of Inspection Activity: No. 1021/24/54, Amendment No. 1

Number of pages: 5

Brno, 13.12.2024

Update: 07.02.2025

Validity till: 12.12.2029


RNDr. Pavel Malčík
Managing Director





NB 1021, Report: 1

Page 2 / 5

1. Information about the manufacturer and about the assessed product

Manufacturer

Dongguan City Xinlijie New Material Co. Ltd

Building 3rd and 4th, No.6 Yinghe Road Guyong, Wanjiang District, Dongguan City, China

1.1 Product description (according to the manufacturer declaration)

Product Name: Vinyl Flooring tiles

Type: Dongguan

Composition: Urethane Acrylate, Polyvinylchloride resin (19 %), Titanium Oxide, Caco 3 (75 %), Carbon Black, Stabilizer, Dot (6 %), Fiber Glass Paper, Modified Epoxy Acrylate, Acrylic Monomers, Fumed silica, Photoinitiators

Thickness: 1.5 - 3.0 mm; **mass per unit area:** 1060 - 2100 g/m²

Tested samples: A) 1.5 mm

B) 3.0 mm

Sampling was carried out by manufacturer. Manufacturer declares no fire retardants or a limiting organic material were used.

1.2 End use application of the product

The classification applies to the following end use application of the product:

- product for full-area covering of floor,
- declared for installation without use of adhesive,
- declared for non-combustible standard substrate represented by fibre cement board.

Testing was performed on sample without use of adhesive, with use of non-combustible standard substrate.

2. Information about the initial testin

2.1 Technical specification

Testing and the assessment of the product are performed to show conformity assessment with the harmonized standard requirements (*system 3 of assessment and verification of constancy of performance – Regulation No. 305/2011, Annex V, Art. 1.4*).

- **EN 14041:2004/AC Resilient, textile and laminate floor coverings – Essential characteristics** (art. 4.1, art. 5.2, Annex ZA).

2.2 Testing methods

Testing of the product was performed according to test methods:

- **EN 13501-1:**
 - **EN ISO 11925-2** Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame – Part 2: Single-flame source test
 - **EN ISO 9239-1** Reaction to fire tests for floorings – Part 1: Determination of the burning behaviour using a radiant heat source
- **EN 717-1, EN 13893**





2.3 Testing results

Testing and assessment of slip resistance was performed on a voluntary basis, by a request of the manufacturer.

2.3.1 Reaction to fire – results

Table No.1 - testin results - reaction to fire art. 4.1		sam le A) 1.5 mm					Results Parameter of fulfilment
Testing method	Characteristic	Value identified (transverse direction)	Value identified (longitudinal direction)				
EN ISO 11925-2	Flame spread:						
ex osure – 15 s	F _s ≤ 150 mm	es	es	es	es	(-)	yes
EN ISO 9239-1	Critical heat flux CF	≥11	≥11	≥11	≥11	≥11	(-)
	(kW.m ⁻²)						
	Smoke (% .minute)	41.0	49.1	32.3	38.4	39.9	

Table No.1b - testin results - reaction to fire (art. 4.1)			sam le B 3.0 mm			
Testing method	Characteristic	Value identified (transverse direction)	Value identified (longitudinal direction)		Average continual arameter m	Results Parameter of fulfilment
EN ISO 9239-1	Critical heat flux CF W.m ⁻²	≥11	≥11	-	-	(-)
	Smoke (% .minute)	34.3	33.7	-	-	

Notice: Notice: If a floor covering is produced with a range of different nominal thickness this needs to be considered when testing. The minimum and maximum thickness (one test each) is tested and complete set of tests for the worst case is carried out. The worst case determines the classification.

For tested scope – sample A) is considered as the worst case. Result is valid for whole scope.

2.3.2 Formaldehyde emission - results

Table No. 2 - testin results - formaldeh de emission art. 4.3)				
Testing method	Characteristic	Requirement	Value identified	Evaluation
EN 717-1	Release of formaldehyde	class		Satisfy
		E1 ... ≤ 0.124 mg/m ³	0.0040 mg HCHO/m ³	(E1)
		E2 ... > 0.124 m m ³		-

2.3.3 Slip resistance - results

Testing and assessment of slip resistance was performed on a voluntary basis, by a request of the manufacturer.

Table No. 3 - testin result – sli resistance art. 4.5				
Testin method	Characteristic	Re uirement	Value identified	Evaluation
EN 13893	Dynamic coefficient of friction -	class DS ... ≥ 0.30	0.51	Satis





3. Classification of construction product and area of direct application

3.1 Reaction to fire

Classification has been performed in compliance with the following articles of EN 13501-1:

- article 12.6 (requirements - class B_f), article 12.9.2 (requirements – s1) and with articles of EN 14041: article 4.1.4 (classification), Annex ZA, article ZA.4

Table No.4 Classification of construction product

Testing method	Characteristic	Requirement	Value identified	Evaluation
EN ISO 11925-2 exposure – 15 s	Flame spread F _s	class B _f F _s ≤ 150 mm	Flame didn't spread more than 150 mm	S
EN ISO 9239-1	Critical heat flux (kW.m ⁻²)	class B _f ≥ 8.0 kW.m ⁻²	≥11	S
	Smoke (% .minute)	class s1 ≤ 750 %.minute	39.9	S

Legend: S – satisfy

Behaviour during burning	Smoke generation		
B _f	s		1

Modification of floor covering classification according to reaction to fire: B_f – s1

3.1.1 Area of application

The present classification applies only for the assessed product with the above specified parameters (see art. 1 of this protocol). The classification applies for the following end use application of the product:

- underlying layer: the type testing results can be used if the density of practical underlying layer is min. 0.75 multiple of density of standard substrate (according to EN 13238, art. 5.1)
- method of laying: laying with or without use of adhesive.

3.2 Formaldehyde emission

The classification has been performed in compliance with the art. 4.3 of the standard EN 14041. On the basis of initial testing result the product shall be declared as formaldehyde class E1.

3.3 Slip resistance

Testing and assessment has been performed by a request of the manufacturer in compliance with table ZA.1. The classification has been performed in compliance with the art. 4.5 of the standard EN 14041. The classification is applicable for floor coverings that are used in dry and non-contaminated conditions.

On the basis of initial testing result the product shall be declared as technical class DS.





NB 1021, Report:

Page 5 / 5

4. Relations of usability

4.1 Limitation

The results of tests and performance assessment apply as long as the conditions remain the same. If the change occurs in the product, the raw material or supplier of the components, or the production process, which would change significantly one or more of the characteristics the tests shall be repeated for the appropriate characteristic.

This Performance assessment protocol is valid till **12.12.2029** provided the technical parameters of product are not changed.

4.2 Usability

The manufacturer can use this protocol for drawing up a Declaration of Performance according to requirements CPR and annex ZA - art. ZA.2.2.2 of the harmonized standard EN 14041. This Declaration of Performance entitles to affix CE marking on the product (according to annex ZA - art. ZA.3 of the standard EN 14041). This protocol issued by Notified Body is only a part of the complete performance assessment.

5. List of documentation for the protocol elaboration

1. Application for testing and classification of the product No. 1041/24 of 04.09.2024, No. 0126/25 of 20.01.2025.
2. Technical documentation of manufacturer (product description).
3. Test protocols issued by the accredited testing laboratory of TZÚ Brno.
 - No. AZL 24/1040 (13.12.2024),
 - No. AZL 25/0126 (06.02.2025),
4. Test report No. MVZ-A-2025-003512 (of 27.01.2025), issued by the accredited testing laboratory of VVÚD Prague.

Protocol issued by:


Lenka Tomková
Notified Body

Protocol checked by:


Svatava Horáčková
Notified Body

