



Hong Kong Eastern Dragon Group Co.,Ltd

A:3# Xiangjiang Road,Huangdao,Qingdao,China PZ:266555

T:008653281833048 F:008653286998264 W:www.chinabestpaper.com

Technical Data Sheet for Brown Kraft Paper

Name of indexes		Substance					
		50 ±2.5	55 ±2.5	65 ±2.5	70 ±2.5	80 ±3	90 ±4
Mass, m ² ,g		50 ±2.5	55 ±2.5	65 ±2.5	70 ±2.5	80 ±3	90 ±4
Stretching strength, kN/m	MD	3.8	4.4	4.7	5.0	5.8	6.5
	CD	2.0	2.3	3.3	3.5	4.0	4.5
Strength index, Nm/g	MD	72	72	72	72	72	72
	CD	50	50	50	50	50	50
Relative lengthening, %	MD	1.7	1.7	1.7	1.7	1.7	1.7
	CD	4.3	4.3	4.3	4.3	4.3	4.3
Break energy, D/m ²	MD	43	48	52	56	64	72
	CD	75	83	91	100	112	126
Energy index, D/m ²	MD	0.8	0.8	0.8	0.8	0.8	0.8
	CD	1.4	1.4	1.4	1.4	1.4	1.4
Index of break resistance mNm ² /g	MD	12	12	12	12	12	12
	CD	12	12	12	12	12	12
Absorbency, g/m ²	WS	30	30	30	30	30	30
Porosity, sec		30	30	30	30	30	30
Air permeance sm ³ /min		>200	>200	>200	>200	>200	>200
Humidity %		7-10	7-10	7-10	7-10	7-10	7-10

Confirmed by EASTERN DRAGON GROUP

Valid date before:31th Dec 2023

