

Appearance	Crystalline white particle
Density (g/cm3)	1.24
Moisture (%)	≤0.05
Monomer content (%)	≤0.3
Melt Flow Index (g/10min) (190C/2.16kg)	9
D-Content (%)	<1
Melting Point (°C)	175
Glass Transition Temperature (°C)	60
Tensile Strength (MPa)	50
Elongation at Break (%)	≤5