



PRODUCT
SPECIFICATION

Ver:	A
DATE:	2023-09-11
DOC No: LY-HN01-09	

LIYUAN BATTERY TECHNOLOGY(Yichun)CO.,LTD
力源电池科技（宜春）有限公司

Add: Liyuan Battery Technology Industrial Park, No.166 Food Avenue, Shanggao
County, Yichun City, Jiangxi Province

CUSTOMER NO:

Specification Approval Sheet
规格确认书

MODEL/型号: INR18650M-3000
(3000mAh 3.6V)

Prepared By/Date 编制/日期	Checked By/Date 审核/日期	Approved By/Date 批准/日期
Xiang Wenbin 2023-09-11	Zhong Miaoxin 2023-09-12	Ma Xujun 2023-09-12

Customer Approval 客户确认	Signature/签字	Date/日期
	Company Name/公司名称	
	Company Stamp/公司印章	



PRODUCT
SPECIFICATION

Ver:	A
DATE:	2023-09-11
DOC No: LY-HN01-09	

Amendment Records/修正记录

Revision 版 本	Description/记 述	Prepared by 编 制	Approved by 批 准	Date/日 期
A	First Publish			



PRODUCT SPECIFICATION

Ver:**A****DATE:****2023-09-11**

DOC No:

LY-HN01-09

Content/目录

1. Scope/适用范围	Page 4
2. Model/型号	Page 4
3.Cell Specification/电芯规格说明	Page 4/5
4. Battery/Cell performance test Criteria/电池性能标准	Page 6
4.1 Appearance inspection by visual/外观目测	Page 6
4.2 Environmental test condition/外界环境条件	Page6
4.3 Electrical characteristics/电气特性	Page 6/7
4.4 Mechanical characteristics/机械特性	Page 7
4.5 Safety performance/安全性能	Page 8
5. Cell initial Dimensions/电芯初始尺寸	Page 9
6. Cautious in Use/谨慎使用	Page 10
7. Period of Warranty/保质期	Page 10
8. Storage of the Batteries/电池的存放	Page 10
9. Other Chemical Reactions/其它化学反应	Page 10
10. Note/注释	Page 10



PRODUCT SPECIFICATION

Ver:	A
DATE:	2023-09-11
DOC No: LY-HN01-09	

1 Scope/适用范围
This specification is applies to describe the related Battery product in this Specification and the Battery/cell supplied by Liyuan Battery Technology (Yichun) Co., Ltd.
本说明书只适用于描述本规格书中相关的产品以及力源电池科技（宜春）有限公司提供的电池。

2 Model/型号: INR18650M-3000

3 Cell Specification/电芯产品规格

No.	Items/项目	Specifications/规格		Remark 备注
1	Nominal Capacity 标称容量	3000mAh		0.2C Standard discharge 0.2C 标准放电
2	Minimum Capacity 最小容量	2950mAh		
3	Nominal Voltage 标称电压	3.6V		Mean Operation Voltage 即工作电压
4	Charge Voltage 充电电压	4.2V±0.03V		By standard charge method 标准充电方式
5	Standard charging method 标准充电方式	0.2C constant current,4.2V constant voltage charge to 4.2V,continue charging till current decline to ≤0.01C		0.2C 恒流 4.2V 恒压充至电流≤0.01C， 时间约 6h(供参考)
6	Fast Charge current 快充电流	0.5C	1500mA	Rapid Charge, charge time about 3h(Ref) 快速充电，时间约 3h(供参考)
7	Standard discharging method 标准放电方式	0.2C constant current discharge to 3.0V		0.2C 恒流放电至 3.0V
8	Cell AC Internal Impedance 单电芯交流内阻	≤60mΩ		Internal resistance measured at AC 1KHz after 50% charge 半电态下用交流法测量内阻
9	Weight 重量	47±2g		



PRODUCT SPECIFICATION

Ver:

A

DATE:

2023-09-11

DOC No:

LY-HN01-09

3 Cell Specification/产品规格(continuous/续上表)

No.	Items/项目	Specifications/规格		Remark 备注
10	Maximum charge current 最大充电持续电流	0.5C	1500mA	For continuous charging mod 连续充电模式
11	Maximum discharge current 最大放电持续电流	1.0C	3000mA	Not for cycle 不适用于循环
12	Operation Temperature and relative humidity Range 工作温度和湿度范围	Charge/充电	0~45℃ 60±25%R.H.	Charge at a very low temperature such as blew -10 ℃ ,will be get a lower capacity and reduce cycle life of the battery 低于-10℃的充电效率会下降, 会影响电池 使用寿命
		Discharge/放电	-20~65℃ 60±25%R.H.	
13	Storage temperature for a long time 长时间储存温度	-20~45℃ 60±25%R.H.		Do not storage exceed half year. Must charge once when storage for half year. Must charge the battery which with protect circuit when storage for three months. 不可超过半年,达到半年须充电一次 带保护板电池 3 个月充电一次

4 Battery/Cell performance test Criteria/电池性能标准

4.1 Appearance inspection by visual/外观目测

There shall be no such defect as rust, leakage, which may adversely affect commercial value of battery.

电池外观应没有锈渍、污渍、漏液等影响商业价值的缺陷存在。

4.2 Environmental test condition/外界环境条件

Unless otherwise specified, all test stated in this product specification are conduct at below test condition

所有测试应按以下环境条件进行, 除非特殊指定外。

Temperature: 25±5℃

Relative Humidity: 60%±25% R.H.



PRODUCT SPECIFICATION

Ver:

A

DATE:

2023-09-11

DOC No:

LY-HN01-09

4.3 Cell Electrical characteristics/电气特性

No	Items/项目	Test Method and Condition/测试方法及条件	Criteria/标准
1	Rated Capacity at 0.2C (Min.) 0.2C 最小额定容量	After standard charge, the capacity shall be measured on 0.2C discharge till the voltage discharge to 3.0V 标准充电后, 放电至 3.0V 截止, 测量 0.2C 放电容量	≥2950mAh
3	Cycle Life 循环寿命	Charging and discharging battery as blew conditions 0.5C standard charge to 4.2V end-off 0.5C standard discharge to 3.0V cut-off Continuous charge and discharge for 300 cycles ,the capacity will be measure after the 300 th cycle 充放电按以下条件: 0.5C 标准充电至 4.2V, 0.5C 标准放电至 3.0V, 连续充放电循环 300 周, 在第 300 周结束后测量容量	≥80% of initial capacity ≥80%初始容量
4	Capacity retention 荷电保持	The battery to be charge in accordance with standard charge condition at 20~30℃, then storage the battery at an ambient temperature 20~30℃ for 28 days. Measure the capacity after 28 days with 0.2C at 20~30℃ as retention capacity. 将电池在 20~30℃标准充电后储存在 20~30℃的环境中 28 天 28 天后, 测试电池在 20~30℃环境下 0.2C 放电容量作为保持容量	Retention capacity 容量保持率≥80% Recovery capacity 容量恢复率≥90%
5	Temperature Dependence of discharge capacity 放电温度特性	Before the battery is tested according to Table 3, it should be charged at room temperature according to the provisions of 3.5, then the battery should be stored at the test temperature for 3 hours, and discharged to 2.75V@0.2 C5A;The capacity of a cell at each temperature shall be compared to the capacity achieved at 25℃ and the percentage shall be calculated. 电池在按表 3 测试前, 应先在常温下按 3.5 规定充电, 然后将电池在测试温度下储存 3 小时, 并以 0.2C5A 放电至 3.0V; 最后将各温度下的容量与 25℃时的容量进行对比, 计算容量百分比	Each cell shall meet or exceed the requirements of Table 3 温度中的放电容量应不小于表 3 的要求



PRODUCT SPECIFICATION

Ver:

A

DATE:

2023-09-11

DOC No:

LY-HN01-09

Table 3 (表 3)

Discharge Temperature 放电温度	-10℃	25℃	40℃
Discharge Capacity/0.2 C ₅ A 放电容量/0.2 C ₅ A	≥75%	≥100%	≥95%

4.4 Mechanical characteristics/机械特性

No	Items/项目	Test Method and Condition/测试方法及条件	Criteria/标准
1	Free fall test 自由跌落测试	The cell to be fully charged in accordance with standard charge condition, then drop the cell three times from a height of 700mm onto a 20mm board. The positive and negative electrode of cell shall be tested once of the XYZ axes 电池按照标准充电条件充满电，然后电池从700mm高度跌落到20mm的硬木板上，每个电池正负极沿着X、Y、Z方向各试验1次。	No smoking, No fire 不冒烟，不起火
2	Vibration test 振动测试	After standard charging, fixed the cell to vibration table and subjected to vibration cycling that the frequency is to be varied at the rate of 1Hz per minute between 16.7Hz, the excursion of the vibration is 2mm. The cell shall be vibrated for 30 minutes per axis of XYZ axes. 将标准充电后的电池固定在振动台上，沿 X、Y、Z 三个方向各振动 30 分钟，振幅 2mm，振动频率为 16.7Hz，每分钟变化 1Hz。	No deformation, No leakage, No explosion , No fire 不变形，不泄漏，不爆炸，不起火

4.5 Safety performance/安全性能

No	Items/项目	Test Method and Condition/测试方法及条件	Criteria/标准
1	130 °C high temperature test 130℃高温测试	Each fully charged cell, stabilized at room temperature, is placed in a circulating air-convection oven. The oven temperature is raised at a rate of 5 °C/min to a temperature of 130 °C ± 2 °C. The cell remains at this temperature for 30 min before the test is discontinued. 充满电的电池温度稳定到常温后，放置入循环空气烘箱里，从常温以 5 °C/分的速率升至 130℃ 后，在 130℃ 放置 30min	No explosion, No fire 不爆炸，不起火



PRODUCT SPECIFICATION


Ver:**A****DATE:****2023-09-11**

DOC No:

LY-HN01-09

No	Items/项目	Test Method and Condition/测试方法及条件	Criteria/标准
2	High and low temperature thermal exposure test 高低温热冲击测试	Each fully charged cell was placed in a low temperature environment at a temperature of -40°C for 1 h, and then left at 85°C for 1 h, the cycle was terminated 32 times. After the test, the sample was taken out and left in the standard environment for 6 h to visually inspect the sample. 充满电的电池放入温度 -40°C 的低温环境中搁置1h, 再在 85°C 条件搁置1h, 如此循环32次结束试验。试验结束后将样品取出, 在标准环境下搁置6h	No leakage, No explosion, No fire 不泄露, 不爆炸, 不起火
3	Short test 短路测试	The fully charged battery is to be short-circuited by connecting the positive and negative terminals of the battery with resistance load not exceed $100\text{m}\Omega$. Tests are to be conducted at room temperature about $25\pm 2^{\circ}\text{C}$. 在室温约为 $25\pm 5^{\circ}\text{C}$ 把充满电的电池的正负极用不超过 $100\text{m}\Omega$ 的负载连接起来, 连接起来使电池外部短路	No explosion, No fire 不爆炸, 不起火
4	Over charge test 过充电测试	After standard charge, continue to charge with a constant voltage $1\text{C}/6.3\text{V}$ per a cell, holding 1h. 电池按标准充满电后, 以 $1\text{C}/6.3\text{V}$ 的恒定电压继续充电, 保持 1 小时	No explosion, No fire 不爆炸, 不起火
5	Over discharge test 过放电测试	After standard discharge, continue to discharge at constant current of 0.2C until the voltage was 0V . 将完全放电态的电池, 以 0.2C 的电流放电至电压为 0V	No explosion, No fire 不爆炸, 不起火
6	Constant temperature damp heat test 恒温湿热测试	The fully charged battery is placed in a constant temperature and humidity chamber with a temperature of $(40\pm 2)^{\circ}\text{C}$ and a relative humidity of 90% to 95% for 48 hours, and is allowed to stand for 6 hours under standard environmental conditions. 将满电的电池放入温度 $(40\pm 2)^{\circ}\text{C}$, 相对湿度 90%~95% 的恒温恒湿箱中, 持续时间 48h, 在标准环境条件下搁置 6h	No leakage, No smoking, No fire 不泄露, 不冒烟, 不起火

5 Cell initial Dimensions/电芯初始尺寸



NO	Items	Units: mm
1	diameter/直径(D)	18.3±0.3
2	Height/高度(H)	65.2±0.3



PRODUCT SPECIFICATION

Ver:

A

DATE:

2023-09-11

DOC No:

LY-HN01-09

6 Cautious in Use/谨慎使用

To ensure proper use of the battery please read the manual carefully before using it.

(为确保正确使用电池, 使用前请仔细阅读本细则)

. Handling (电池操作)

- Do not expose to, dispose of the battery in fire. (不要靠近和放置电池于火中)
- Do not put the battery in a charger or equipment with wrong terminals connected. (在充电器或设备仪器中不要把电池接错电极)
- Avoid shorting the battery (避免电池短路)
- Avoid excessive physical shock or vibration. (避免电池过多的物理撞击和震动)
- Do not disassemble or deform the battery. (不要解剖和使电池变形)
- Do not immerse in water. (不要把电池浸泡在水中)
- Do not use the battery mixed with other different make, type, or model batteries. (不要和其它不同类型的电池混和使用)
- Keep out of the reach of children. (放置电池于儿童不易接触的地方)

. charge and discharge (充电和放电)

- Battery must be charged in appropriate charger only. (电池必须用适当的充电器充电)
- Never use a modified or damaged charger. (不要使用改装或损坏的充电器)
- Do not leave battery in charger over 24 hours. (不要把电池放置于充电器超过 24h)

. storage(储存)

- Store the battery in a cool, dry and well-ventilated area. (应把电池置于凉爽、干燥及通风良好的区域)

. disposal (电池处理)

- Regulations vary for different countries. Dispose of in accordance with local regulations. (电池处理要符合当地的规定)

7 Period of Warranty/保质期

The period of warranty is one year from the date of shipment. Great Power guarantees to give a replacement in case of cells with defects proven due to manufacturing process instead of the customer abuse and misuse.

电池的保质期从出货之日算起为一年。如果电池的缺陷是在制造过程中形成的而不是由于用户滥用及错误使用造成, 本公司负责退换电池。

8 Storage of the Batteries/电池的存放

The batteries should be stored at room temperature, charged to about 30% to 50% of capacity.

电池应当在室温下存放, 应充到 30%至 50%的电量。

We recommend that batteries be charged about once per half a year to prevent over discharge.

如长时间储存, 建议每半年充一次电以防止电池过放电。

9 Other Chemical Reactions/其它化学反应

Because batteries utilize a chemical reaction, battery performance will deteriorate over time even if stored for a long period of time without being used. In addition, if the various usage conditions such as charge, discharge, ambient temperature, etc. are not maintained within the specified ranges the life expectancy of the battery may be shortened or the device in which the battery is used may be damaged by electrolyte leakage. If the batteries cannot maintain a charge for long periods of time, even when they are charged correctly, this may indicate it is time to change the battery.

由于电池是利用化学反应的原理, 所以随着时间的增加电池的性能会降低, 即使是存放很长一段而不使用。如果使用条件如充电、放电及周围环境温度等情形不在指定的使用范围内, 会使缩短电池的使用寿命, 或者会产生漏液导致设备损坏。如果电池长周期不能充电, 即使充电方法正确, 这样需要更换电池了。

10 Note/注释

Any other items which are not covered in this specification shall be agreed by both parties.

本说明书未包括事项应由双方协议确定。