

YANGZHOU YILIKIM NEW MATERIALS TRADING CO., LTD.

NO. 5 ROAD, EAST AUTOMOTIVE INDUSTRIAL PARK YANGZHOU,
YIZHENG, JIANGSU P.R.OF CHINA 211400
Tel:0514-83420672 Fax:0514-83410116
Email: cynthiazhang@yilikim.com

TYPICAL VALUE FOR PLA RESIN

Test Item	Unit	FY802 SPEC
Exterior		Transparent or translucent particles
Density	g/m ³	1.24
Moisture	%	0.04
Monomer Content	%	≤0.3
Melt Flow Index (190℃)	g/10min	4
D-Content	%	2
Melting Point	℃	165
Glass Transition Temperature	℃	60
Tensile Strength	MPa	50
Elongation at Break	%	≤5