

### Properties Range

Characteristics		Unit	Spec	Test Method	
Dimension	Thickness	Tempered Glass (Asahi / Gorilla / Schott)	mm	0.33±0.05	Micrometer Method
		AB Adhesive	mm	0.36±0.02	
Optical Properties	Transmittance(550nm)		%	≥91.5%	JIS K7136
	Haze(380~760nm)			≤0.3%	
Mechanical Properties	Contact angle		°	≥100	Theta QC
	Impact Strength (Steel ball:30g)		mm	350	Ball Drop Test
	Hardness		H	10	JIS K5600
	Adhesion		mN/25mm	40	JIS K5600
	X-Cutting(Cross hatch)		-	100/100	JIS K5600
	Paricle		-	Pass(Clear)	FS Method