

| TECH SPECS               |                                                  |
|--------------------------|--------------------------------------------------|
| 1. Glass Thickness:      | 0.33 mm                                          |
| 2. Glass Material        | CSG Alumino-Silicate Glass                       |
| 3. Strength Technology   | 2x Hydrofluoric acid / Normal                    |
| 4:Glue                   | Toyo AB Glue                                     |
| 5:Glue Thichness         | 0.25 mm                                          |
| 6. AF Test               | 3000 Times under 500g pressure (Steel Wool Ball) |
| 7.Droplet Angel          | 100° ~ 115°                                      |
| 8. Tempered Time         | A: Heating Tempered Oven: 1H                     |
|                          | B:Tempered Time: 4 Hours                         |
| 9. Tempered Temperature: | 380 ~ 400℃                                       |
| 10.AF Oil                | Dakin 5‰                                         |
| 11.Transparency          | ≥92%                                             |