

Items \ Grade	C	B	A	AA
Quality (The proportion of wood pulp)	100% Virgin wood pulp	100% Virgin wood pulp	100% Virgin wood pulp	100% Virgin wood pulp
BRIGHTNESS (%) is greater than	96-98	100-102	102-104	104-106
CIE WHITENESS (%)	140-150	140-150	150-160	160-170
ROUGHNESS(%)	75-150	75-150	75-150	75-150
STIFFNESS L & OW, MD(%)	>110	>110	>110	>110
STIFFNESS L & W, CD(%)	>50	>50	>50	>50
Opacity (%)	>95	>95	>95	>95
Smoothness (%) is greater than	Recto25	Recto25	Recto25	Recto25
	Wire side20	Wire side20	Wire side20	Wire side20
Recto and wire side deviation is less than(s)	30	30	30	30
Size resistance(mm)is greater than	0.75	0.75	0.75	0.75
Ash content (%)	16---18	16---18	16---18	16---18
Moisture content (%)	4.5---5.5	4.5---5.5	4.5---5.5	4.5---5.5
Density (g/cm3) less than the	0.75	0.75	0.75	0.75
Surface strength (m / s) is greater than	1.0	1.0	1.0	1.0
Dust degree (a / m2) is less than	(0.2—1.5) mm2 50	(0.2—1.5) mm2 50	(0.2—1.5) mm2 50	(0.2—1.5) mm2 50
	Greater than1.5mm20	Greater than1.5mm20	Greater than1.5mm20	Greater than1.5mm20
Substance deviation is less than (g)	2.5	2.5	2.5	2.5
Thickness (um)	105—115	105—115	105—115	105—115
Thickness deviation is less than (um)	0.5	0.5	0.5	0.5