



QINGDAO PARTNER IMP AND EXP. CO., LIMITED

GENERAL ADMINISTRATION BUILDING , No. 9 LIAOYANG
EAST ROAD, LAOSHAN DISTRICT, QINGDAO CHINA

WWW.PARTNERGLASS.CN

SAMPLE TIME	Thickness	TESTED T	VisiVle		NM	%
			T%	T% 转5 mm	MAX WAVELENGTH	700NM Transmittance
2019-05-05	2.9	2.828	90.8	89.77	520	88.4
2019-05-06	4	3.833	90.51	90.01	520	87.23
2019-05-11	5	4.807	90.27	90.19	520	86.28
2019-06-21	6	5.84	89.61	89.97	510	83.95
2019-06-26	8	7.746	89.1	90.17	520	82.49
2019-04-16	10	9.761	88.17	90.09	510	79.26
2019-04-13	12	11.529	87.48	90.1	510	76.72
2019-04-12	15	14.477	86.39	90.12	510	73.12
2019-04-07	19	18.774	84.85	90.15	510	63.35