

Steel Fibre

| Commodity | Type | Length (mm) | Diameter (mm) | L/D | Tensile Strength (MPa) |
|---------------------------------|---|-------------|---------------|-----|------------------------|
| Hooked-End Steel Fibre | HF05020 | 20 | 0.5 | 40 | 1050/1150 |
| | HF05030 | 30 | 0.5 | 60 | |
| | HF05530 | 30 | 0.55 | 55 | |
| | HF05535 | 35 | 0.55 | 64 | |
| | HF06030 | 30 | 0.6 | 50 | |
| | HF07560 | 60 | 0.75 | 80 | |
| | HF07530 | 30 | 0.75 | 40 | |
| | HF07535 | 35 | 0.75 | 47 | |
| | HF09050 | 50 | 0.9 | 56 | |
| | HF09060 | 60 | 0.9 | 67 | |
| | HF10050 | 50 | 1 | 50 | |
| | HF10060 | 60 | 1 | 60 | |
| Glued Steel Fibre | GS04-60/60 | 60 | 1 | 60 | 1100 |
| | GS04-65/60 | 60 | 0.9 | 67 | |
| | GS04-80/60 | 60 | 0.75 | 80 | 1150 |
| | GS04-80/50 | 50 | 0.62 | 81 | 1200 |
| | GS04-55/35 | 35 | 0.62 | 56 | |
| | GS04-65/35 | 35 | 0.55 | 64 | |
| | GS04-50/25 | 25 | 0.5 | 50 | 1300 |
| Flat Ends Steel Fibre | FF05020 | 20 | 0.5 | 40 | 1050 |
| | FF05030 | 30 | 0.5 | 60 | |
| | FF05530 | 30 | 0.55 | 55 | |
| | FF05535 | 35 | 0.55 | 64 | |
| | FF06030 | 30 | 0.6 | 50 | 1000 |
| | FF07530 | 30 | 0.75 | 40 | |
| | FF07535 | 32 | 0.75 | 47 | |
| | FF09050 | 50 | 0.9 | 56 | |
| | FF10050 | 50 | 1 | 50 | |
| Waved Steel Fibre | WF05020 | 20 | 0.5 | 40 | 800-1150 |
| | WF05030 | 30 | 0.5 | 60 | |
| | WF05530 | 30 | 0.55 | 55 | |
| | WF05535 | 35 | 0.55 | 64 | |
| | WF06030 | 30 | 0.6 | 50 | |
| | WF07530 | 30 | 0.75 | 40 | |
| | WF07535 | 32 | 0.75 | 47 | |
| | WF09050 | 50 | 0.9 | 56 | |
| | WF10050 | 50 | 1 | 50 | |
| Copper Coated Micro Steel Fibre | MF | negotiation | 0.15-0.25 | - | 2850 |
| Packing | in compound kraft paper bags with inner two in one film bags of 20Kg or 25Kg net each, 1200Kg on pallet | | | | |
| Remarks | 1. Steel Fibre could be applied in ASTM A820 TYPE I standard; HF10050 conforms with CE Certificate DS/EN 14889-1 2. Special Steel Fibre is available according to the buyer's requirements (tensile strength, thickness, width, length, diameter etc.) | | | | |