

TEL:054-933-1422

FAX:054-931-1420

Test Report

Grade:EMPP TPO 52AI(UV) BK

Material Type: PP + RUBBER + TALC + UVstabilizer

Property	Test Method	Test Conditions	UNIT	Result
Specific Gravity	ASTM D792	23 도 상온	g/10min	1.02
Melt Index	ASTM 1238	230°C. 2.16kg	—	43
Tensile Elongation	ASTM D638	50mm/min	%	113
Impact Strength(23°C)	ASTM D256	Notched(1/4")	J/M	414
Tensile Strength	ASTM D638	50mm/min	MPa	17.0
Flexural Modulus	ASTM D790	1/4"SPAN,5mm	MPa	1780
Flexural strength	ASTM D790	1/4"SPAN100,5mm	MPa	24

※ The above physical properties are self-measured results and may change depending on processing conditions.

Q.A: MK . JANG



Innovation Chemical.co.ltd

