



Hong Kong Eastern Dragon Group Co.,Ltd

A:3# Xiangjiang Road,Huangdao,Qingdao,China PZ:266555

T:008653281833048 F:008653286998264 W:www.chinabestpaper.com

Technical Data Sheets

Machine: PM3

Item: Photocopy paper

Super Dragon

Item	Unit	Standard	Result
Basic Weight	g/m2	ISO 536	75
Thickness	mm/1000	ISO 534	100.5
Bending stiffness	CD/MN	ISO 2493	128/63
Surface roughness BS	ml/min	ISO 8791-2	200
CIE Whiteness	%	ISO 11475	167
UV Whiteness	%	ISO 2470	110
Opacity	%	ISO 2471	min 90.5
Moisture	%	ISO 287:1994	3,8-5,0

Eastern Dragon

Item	Unit	Standard	Result
Basic Weight	g/m2	ISO 536	75
Thickness	mm/1000	ISO 534	99.4
Bending stiffness	CD/MN	ISO 2493	125/60
Surface roughness BS	ml/min	ISO 8791-2	200
CIE Whiteness	%	ISO 11475	160
UV Whiteness	%	ISO 2470	103
Opacity	%	ISO 2471	min 90.5
Moisture	%	ISO 287:1994	3,8-5,0

Golden Dragon

Item	Unit	Standard	Result
Basic Weight	g/m2	ISO 536	75
Thickness	mm/1000	ISO 534	99.4
Bending stiffness	CD/MN	ISO 2493	120/55
Surface roughness BS	ml/min	ISO 8791-2	200
CIE Whiteness	%	ISO 11475	150
UV Whiteness	%	ISO 2470	96
Opacity	%	ISO 2471	min 90.5
Moisture	%	ISO 287:1994	3,8-5,0

Validate: Before 31st Dec 2022

