



Hong Kong Eastern Dragon Group Co.,Ltd

A:3# Xiangjiang Road,Huangdao,Qingdao,China PZ:266555

T:008653281833048 F:008653286998264 W:www.chinabestpaper.com

Technical Data Sheet(Photo copy paper 80gsm)

Super Dragon Grade

Item	Unit	Standard	Result
Basic Weight	g/m2	ISO 536	80
Thickness	mm/1000	ISO 534	109
Bending stiffness	CD/MN	ISO 2493	145/68
Surface roughness BS	ml/min	ISO 8791-2	170
CIE Whiteness	%	ISO 11475	165
UV Whiteness	%	ISO 2470	113
Opacity	%	ISO 2471	>= 94
Moisture	%	ISO 287:1994	3,8-5,0

Eastern Dragon Grade

Item	Unit	Standard	Result
Basic Weight	g/m2	ISO 536	80
Thickness	mm/1000	ISO 534	103
Bending stiffness	CD/MN	ISO 2493	125/60
Surface roughness BS	ml/min	ISO 8791-2	150
CIE Whiteness	%	ISO 11475	145
UV Whiteness	%	ISO 2470	110
Opacity	%	ISO 2471	min 92
Moisture	%	ISO 287:1994	3,8-5,0

Golden Dragon Grade

Item	Unit	Standard	Result
Basic Weight	g/m2	ISO 536	80
Thickness	mm/1000	ISO 534	102
Bending stiffness	CD/MN	ISO 2493	122.5/55
Surface roughness BS	ml/min	ISO 8791-2	140
CIE Whiteness	%	ISO 11475	155
UV Whiteness	%	ISO 2470	103.5
Opacity	%	ISO 2471	min 90
Moisture	%	ISO 287:1994	3,8-5,0

