



Hong Kong Eastern Dragon Group Co.,Ltd

A:3# Xiangjiang Road,Huangdao,Qingdao,China PZ:266555

T:008653281833048 F:008653286998264 W:www.chinabestpaper.com

Quality Inspection Report

Super Dragon

Parameters	48.8 g
Basis weight, g/m ²	48.8 +/-1.7
Fiber mix	TMP - 15% Broke - 0% Pulp - 10-12% SGW - the rest
Brightness, %	min 64
Thickness, mm	max 0.085
Density, g/cm ³	min 0.57
Bulk, cm ³ /g	max 1.75
Moisture content, %	8.5 +/-1.5
Tear resistance in CD, mN	min 230
Opacity,%	min 94
Smoothness (Bekk), sec	45 +/- 10
Breaking length in MD, m	min 3800
Porosity (Bentsen), ml/min	max 250
Elongation, %	min 0.9
Shade	a = - 0.35 +/- 0.15 b = 3.5 +/- 0.5

Eastern Dragon

Parameters	48.8 g
Basis weight, g/m ²	48.8 +/- 1.7
Fiber mix	TMP - 15% Broke - 0% Pulp - 10-12% SGW - the rest
Brightness, %	min 60
Thickness, mm	max 0.08
Density, g/cm ³	min 0.57
Bulk, cm ³ /g	max 1.75
Moisture content, %	8.5 +/-1.5
Tear resistance in CD, mN	min 220
Opacity,%	min 90
Smoothness (Bekk), sec	40 +/- 10
Breaking length in MD, m	min 3000
Porosity (Bentsen), ml/min	max 250
Elongation, %	min 0.7
Shade	a = - 0.35 +/- 0.15 b = 3.5 +/- 0.5