



TECHNICAL INFORMATION

Shenzhen JinHua
Quality & Value

Epoxy Resin 318AB-7T

Feature

Epoxy resin 318AB-7T can be cured under normal temperature and high temperature, with the feature of good flowing property, low viscosity, very little heat release, natural defoaming, anti-yellow, high transparency, no ripple, bright in surface.

Application

318AB-7T specially designed for large size wood table casting, lamp potting and mold filling, etc..

Properties before Hardening

Part	318A-7T	318B-7T
Color	Transparent	Transparent
Specific gravity	1.15	0.97
Viscosity (25°C)	2000-4000CPS	50 MAXCPS
Mixing ratio	A: B = 100:33(weight ratio)	
Hardening conditions	25 °C×24H-48H (100 g)	
Usable time	25°C×120min (100g)	

Operation

- 1.Weigh A and B glue according to the given weight ratio into the prepared cleaned container, fully mixed the mixture again the container wall by clockwise, place it along for 3 to 5 minutes, and then it can be used.
- 2.Take the glue according to the usable time and dosage of mixture to avoid wasting. When the temperature is below 15 °C, please heat A glue to 30 °C first and then mix it to the B glue (A glue will be thicken in low temperature); The glue must be sealed lid after use to avoid rejection caused by moisture absorption.
- 3.When the relative humidity is higher than 70%, the surface of the cured mixture will absorb moisture in the air, and form a layer of white mist in the surface, so when the relative humidity is higher than 70%, is not suitable for room temperature curing, suggest to use the heat curing.

Properties after Hardening

Hardness, shore D	<86
Withstand voltage, KV/mm	22
Flexural strength, Kg/mm2	28
Volume resistivity, Ohm3	1x10 ¹⁵
Surface resistance, Ohmm2	5X10 ¹⁵
Thermal conductivity, W/M.K	1.36

Add: Yufeng Industrial Park, Jiangshi Road, Guangming New District, Shenzhen, China
Tel: +86-0755-27131499 Fax: +86-0755-27128202 Email:sales@jinhuauglue.com



TECHNICAL INFORMATION

Shenzhen JinHua Quality & Value

Induced electric loss, 1KHZ	0.42
Withstand high temperature, °C	80
Moisture absorption, %	<0.15
Compressive strength, Kg/ mm ²	8.4

Caution

- 1, The operating environment should be ventilative and should keep away from fire. Closely sealed after use.
- 2, Avoid eye contact, in case of contact, wash with plenty of water and get medical attention immediately.
- 3, If contact skin, wrap with clean cloth or paper, and wash it with water and soap.
- 4, Keep away from children.
- 5, Please take a trial before application to avoid usage mistake.

Storage And Shelf Life

- 1, Store at the temperature of 25°C or cool and dry place. Avoid from sunlight, high temperature or high humidity environment.
- 2, Use up as soon as possible when opened. It is strictly forbidden to expose to the air for a long time after it is opened to avoid affecting the quality of the products. The shelf life is six months in the room temperature of 25°C.

Notice: The above data is typical data measured by the laboratory environment under the temperature of 25 °C, and humidity of 70%. For customers' reference only.